

PP

- Temperature print: 250 - 270 °C for 2,90 mm filament / 220-250 °C for 1,75 mm filament
- Temperature pad is 70 – 90 °C

Material data sheet for PP:

Property	Value	Unit
MFR 230/2.16 ISO 1133	5,44	g/10 min
Yellow Index Pell. BTM20032	-8,10	
Film Rating App. MTM17108	0,0	
Fish Eyes 1.5-2.5 mm MTM17108	0,0	
Fish Eyes 0.7-1.5 mm MTM17108	0	
Fish Eyes 0.5-0.7 mm MTM17108	0	
Fish Eyes >0.2 mm MTM17108	65	

The above particulars do not release the customer from the obligation to carry out an inspection of goods received.

Basell Sales & Marketing Company B.V.

This report is not to be signed.

Our Quality Management System is certified.